

EMSL Analytical, Inc.

2205 Corporate Plaza Parkway SE, Suite 200 Smyrna, GA 30080

Tel/Fax: (770) 956-9150 / (770) 956-9181 http://www.EMSL.com / atlantalab@emsl.com EMSL Order: 071706444

Customer ID: RENE99

Customer PO: Project ID:

Attention: AIR ALLEGEN AND MOLD TESTING, INC.

Air Allergen & Mold Testing

1543 Lilburn Stone Mountain Rd

Suite 200

Stone Mountain, GA 30087

Project: 75TED - 16207

Phone: (770) 938-4861

Fax: (770) 270-0853

Received Date: 10/16/2017 8:15 AM

Analysis Date: 10/16/2017

Collected Date: 10/13/2017

Test Report: Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

		Non-Asbestos			<u>Asbestos</u>
Sample	Description	Appearance	% Fibrous	% Non-Fibrous	% Type
TL-01-01-Floor Tile	12x12 Tile/Mastic Brown	Brown Non-Fibrous		93% Non-fibrous (Other)	7% Chrysotile
071706444-0001		Homogeneous			
TL-01-01-Mastic	12x12 Tile/Mastic Brown	Black Non-Fibrous		95% Non-fibrous (Other)	5% Chrysotile
071706444-0001A		Homogeneous			

Analyst(s)

Anthony Sanaie (2)

(b) (6)

Amber Baynes, Asbestos Lab Supervisor or Other Approved Signatory

EMSL maintains liability limited to cost of analysis. This report relates only to the samples reported and may not be reproduced, except in full, without written approval by EMSL. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. This report must not be used by the client to claim product certification, approval, or endorsement by NVLAP, NIST or any agency of the federal government. Non-friable organically bound materials present a problem matrix and therefore EMSL recommends gravimetric reduction prior to analysis. Samples received in good condition unless otherwise noted. Estimated accuracy, precision and uncertainty data available upon request. Unless requested by the client, building materials manufactured with multiple layers (i.e. linoleum, wallboard, etc.) are reported as a single sample. Reporting limit is 1%

Samples analyzed by EMSL Analytical, Inc Smyrna, GA NVLAP Lab Code 101048-1

Initial report from: 10/16/2017 11:01:26